

Technical data sheet

Aquasit cold casting compound, mixing bag

Item number: 2363036



Two-component casting compound Aquasit in an aluminium bag, for filling junction boxes in outdoor areas exposed to high levels of and long-lasting dampness. Also applicable for mechanical shock.

Processing time of 20 minutes after opening and mixing. Can be stored unopened at 0 to 40 °C up to 24 months from date of production. Practical experience, tests and approvals only apply in conjunction with OBO junction boxes.

Protection rating with appropriate junction box: IP68
Rated voltage: 400 V
Penetration resistance: >25 kV/mm to VDE 0291 Part 2
Operating temperature: -40 to +80 °C
Processing temperature: 5 to +40 °C
Halogen-free, silicon-free, isocyanate-free
Environmentally friendly and without the need to be labelled



Master data

Item number	2363036
Type	KVMM 1600
Description 1	Aquasit
Description 2	cast.compound for junct. boxes
Manufacturer	OBO
Dimension	1600 ml
Smallest sales unit	1
Unit of quantity	Piece
Weight	150 kg
Weight unit	kg/100 pc.

Dimensions

Length	330 mm
Width	210 mm
Height	52 mm

Technical data

For Ex zone	Without
For Ex zone gas	Without
For Ex zone dust	Without

Technical data sheet

Aquasit cold casting compound, mixing bag

Item number: 2363036



Technical data

Contents	1600 g
Contents	1600 ml
Storage options in months	24
Material cable resin	Two-component polyurethane resin